STONEBRIDGE
COATINGS LABORATORY, INC.

September 21, 2017

Thomas Plotzner
Odenwald Faserplattenwerk GmbH
D-63916 Amorbach
E-Mail thomas.ploetzner@owa.de

Re.: **Test Report No. 117_104B – Washability Testing of Coated Tiles according to ASTM D4828**

Dear Mr. Plotzner:

We have completed the washability testing of your ***OWAcoustic Scrim Laminated Mineral Tile*** ceiling tiles per ***ASTM D4828****, Practical Washability of Organic Coatings*. Tiles were lightly dusted with a carbon black pigment to simulate household dirt. They were cleaned with a damp sponge and non-abrasive cleaner using a linear abrasion tester. **After 100 cycles, the stain/dirt was partially removed leaving the stained area slightly visible for a rating of 5 as per the method (see below).** Annex 1 shows a stained tile before and after washing.

ASTM D4828 Stain Removal Ratings:

10	All soil and stain removed
7	Large change from original, barely visible
5	Moderate change from original, slightly visible
3	Slight change from original, but readily visible
0	No change from original intensity (depth) of soil or stain

We thank you for the opportunity to assist you in your testing needs.

Sincerely,

Debora L. Hense

Technical Manager